

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

Claims 1-9. (cancelled).

10. (previously presented) A concentrate comprising (percentages by weight):
  - A) from 40% to 95% of a composition relative to the total weight of A) comprising:
    - 1) from 10% to 35% of polybutene-1, wherein the polybutene-1 comprises a melt flow rate ranging from 100 to 1000 g/10 min., measured at 190°C at 2.16 kg;
    - 2) from 90% to 65% of polypropylene; and
  - B) from 5% to 60% of one or more additives.
11. (previously presented) The concentrate according to claim 10, wherein the concentrate comprises from 50% to 95% by weight of the composition relative to the total weight of A).
12. (previously presented) The concentrate according to claim 10, wherein the concentrate comprises from 60% to 80% by weight of the composition relative to the total weight of A).
13. (previously presented) The concentrate according to claim 10, wherein the composition comprises from 25% to 35% by weight of polybutene-1.
14. (previously presented) The concentrate according to claim 10, wherein the composition comprises from 30% to 35% by weight of polybutene-1.
15. (previously presented) The concentrate according to claim 10, wherein the composition comprises from 75% to 65% by weight of polypropylene.
16. (previously presented) The concentrate according to claim 10, wherein the composition comprises from 70% to 65% by weight of polypropylene.

17. (previously presented) The concentrate according to claim 10, wherein the composition comprises from 5% to 50% by weight of one or more additives.

18. (previously presented) The concentrate according to claim 10, wherein the composition comprises from 20% to 40% by weight of one or more additives.

19. (previously presented) The concentrate according to claim 10, wherein the polybutene-1 is a linear, semicrystalline and highly isotactic homopolymer.

20. (previously presented) The concentrate according to claim 10, wherein the polypropylene is isotactic polypropylene having an index of isotacticity greater than or equal to 90.

21. (previously presented) The concentrate according to claim 10 for dispersing one or more additives in at least one polyolefin.

22. (previously presented) Polyolefinic articles comprising the concentrate of claim 10, wherein the concentrate is blended with at least one polyolefin and then processed.

23. (previously presented) Coloured polypropylene fibres comprising the concentrate of claim 10, wherein the concentrate is blended with at least one polyolefin and then spun.

24. (previously presented) A polyolefinic composition for preparing concentrates of additives, comprising (percentages by weight):

- a) from more than 10% to 35% of polybutene-1 comprising a melt flow rate ranging from 100 to 1000 g/10 min., measured at 190°C at 2.16 kg; and
- b) from less than 90% to 65% of polypropylene.

25. (previously presented) The polyolefinic composition of claim 24 comprising from 25% to 35% by weight of polybutene-1.

26. (previously presented) The polyolefinic composition of claim 24 comprising from 30% to 35% by weight of polybutene-1.

27. (previously presented) The polyolefinic composition of claim 24 comprising from 75% to 65% by weight of polypropylene.

28. (previously presented) The polyolefinic composition of claim 24 comprising from 70% to 65% by weight of polypropylene.

29. (previously presented) The concentrate of claim 10, wherein the polybutene-1 comprises a melt flow rate ranging from 100 to 400 g/10 min., measured at 190°C at 2.16 kg.

30. (canceled)

31. (canceled)

32. (canceled)

33. (previously presented) The concentrate of claim 10, wherein the additives are selected from at least one pigment, colorant, or mixture thereof.

34. (cancelled)

35. (currently amended) A concentrate [~~according to claim 34~~] consisting essentially of (percentages by weight):

A) from 40% to 95% of a composition relative to the total weight of A) consisting essentially of:

1) from 10% to 35% of polybutene-1, wherein the polybutene-1 comprises a melt flow rate ranging from 100 to 1000 g/10 min., measured at 190°C at 2.16 kg;

2) from 90% to 65% of polypropylene; and

B) from 5% to 60% of one or more additives.